

TECHNICAL DATA SHEET

DEKASYL MS-2 ELASTIC ADHESIVE & SEALANT

PRODUCT

Dekasy MS-2 is a good compromise between an adhesive and a sealant. **Dekasy MS-2** is suitable for making elastic constructive joints, which also require a high strength. **Dekasy MS-2** is based on MS Polymer.

APPLICATIONS

- Elastic bondings and sealings in e.g. caravan- and camper construction.
- Bonding of roofs on busses, caravans and campers.
- Bonding of corner profiles of aluminium or polyester on trailers.
- Bonding of polyester parts on metal frames.
- Bonding of floor systems.
- Sealing welded seams.

FEATURES

- Solvent-, isocyanate- and PVC free.
- Very good UV-resistance and ageing properties.
- In general good adhesion on several substrates without the use of a primer, e.g. **Dekasy MS-2** can be used as a sealant on PVC floorings.
- Permanent elastic within temperatures from -40°C till $+120^{\circ}\text{C}$.
- Neutral, odourless and fast curing.
- Paintable after skin forming (wet on wet); this will in general not influence the curing speed.
- Paint compatible with most industrial paint- or lacquer systems, both alkyd resin and dispersion based (due to the large scale of different types of industrial paints a paint compatibility test is recommended!)

ADHESION

In general **Dekasy MS-2** adheres well without primer on clean, dry, dust- and grease free substrates of aluminium, stainless steel, galvanised steel, zinc, copper, brass, powder coated metal, most lacquered metal surfaces, glass, PVC, polyester (GRP), painted and lacquered wood, etc. No adhesion on untreated polyethylene, polypropylene and teflon. In those cases where due to great thermal or physical loads, especially under wet conditions, high adhesion demands are needed, the use of an adhesion promotor is recommended. For not mentioned substrates and additional information consult Dekalin.

METHOD OF USE

Dekasy MS-2 can easily be extruded with a hand- or air pressure gun at temperatures between $+5^{\circ}\text{C}$ and 35°C . In sealing applications **Dekasy MS-2** should be tooled or smoothened within 10 minutes (at $20^{\circ}\text{C}/50\%\text{R.H.}$) with a spatula or putty knife, occasionally moistened with a mild soap solution. Avoid soap solution penetrating between joint sides and sealant, because this will create loss of adhesion. In bonding applications the substrates have to be assembled within 15 minutes (at $20^{\circ}\text{C}/50\%\text{R.H.}$) after applying **Dekasy MS-2**. The higher the temperature, the shorter the open time will be! In general an adhesive thickness of 2 mm is recommended if similar materials (similar stiffenesses) are bonded. The larger the difference in thermal expansion is, the thicker the adhesive bead should be. For more details Dekalin should be consulted. At a temperature of 20°C and a relative humidity of 50% **Dekasy MS-2** can be painted with the most industrial paints already 10 minutes after application. Best adhesion of paint coats is generally obtained if painted within 4 hours after applying **Dekasy MS-2**. Cleaning tools or removing uncured residue of Dekasy MS-2 can be done with a clean colourless cloth, wetted with e.g. acetone or MEK. It is recommended to make a trial first to check possible attack of the substrate by these cleaners.

TECHNICAL DATA SHEET**TECHNICAL DATA**

Basic material	: MS Polymer
Curing method	: moisture
Specific density (20°C)	: ca. 1.4 g/ml
Skin forming time (20°C/50% R.H.)	: ca. 10 min.
Open time (20°C/50%R.H.)	: < 15 min.
Curing speed after 24 hrs (20°C/50%R.H.)	: ca. 3 mm
Shore A hardness (DIN 53505)	: ca. 55
Volume change (DIN 52451)	: < 3%
Green strength (Physica Rheometer MC100)	: ca. 300 Pa
(max. load which can be applied per m ² uncured adhesive without sagging)	
Tensile stress (100%) (DIN 53504/ISO 37)	: ca. 1.7 MPa
Tensile stress at break (DIN 53504/ISO 37)	: ca. 2.6 MPa
Elongation at break (DIN 53504/ISO 37)	: ca. 250%
Shear stress (DIN 53283/ASTM D1002)	: ca. 2.5 MPa
(Alu-Alu; adh. thickness 2mm; test speed 50 mm/min.)	
Tear propagation (DIN 53515/ISO 34)	: ca. 16 N/mm
(Type C, test speed 500 mm/min.)	
Solvent percentage	: 0%
Isocyanate percentage	: 0%
Temperature resistance	: - 40°C till +120°C
Temperature resistance (max. 20 minutes)	: +180°C
Application temperature	: +5°C till +35°C
UV- and weather resistance	: excellent
Colours (standard)	: white, grey, black
Packaging	: 290 ml cartridges, 600 ml bags, other packaging on request.

STORAGE STABILITY

Dekasyl MS-2 may be stored for 12 months in a closed (unopened) packaging in a dry place at temperatures between +5°C and +30°C (cartridges 18 months).

SAFETY PRECAUTIONS

No specific safety precautions required. Consult safety data sheet.

TRANSPORT CLASSIFICATION

Not applicable.

©Dekalin November, 2013